

Hot Stamping-Metallic-RS-01

Hot Stamping Transfer Product for rough material surfaces with good coverage and very high gloss



Characteristic

- For medium to flat embossing motifs
- Good performance on substrates with rough surfaces
- Excellent for flat embossing motifs
- Suitable for embossing / debossing
- Very high gloss

Areas of application

- Suitable for bookbinding materials
- Embossed substrates
- Substrates with very rough surfaces
- Coated and uncoated papers and cardboards
- Printed and unprinted papers and cardboards
- Flock fiberboard (cotton flannel)
- Artificial leather

Processing parameters

- Vertical, platen and clam-shell machines: 90 °C - 130 °C
- Cylinder presses: 130 °C - 150 °C

Available colors




● G-220



● S-01



○ MS-01



● MG-123

● Standard product. Mostly on stock.

○ These products are available on order. Small quantities may be available. A minimum order quantity applies.

The colors shown here are for reference only, are technically generated and not binding. Please ask for one of our original color guides for this product. Other colors and gloss levels are available on request.

Formats

Core size

1 inch cardboard and plastic core
and 3 inch cardboard core

Product width

A few millimeters to more than
one meter possible

Running meters per roll

Depending on winding and material
thickness up to 6,000 meters
possible

Certificates

**REACH
SVHC**

94/62/EC



Under optimum transfer conditions, all our products have a high to very high gloss (except satin and matt products) and high abrasion and rub resistance. However, as these values depend on many production parameters and not least on the substrate and printing process used, we cannot give any measured values here.

All Univacco products have been developed for their respective specific applications. However, experience shows that substrates, printing machines and operating conditions can vary. Therefore, users of our products are urged to verify that the selected product types are suitable for their specific applications by making test prints under production conditions. For this purpose, samples are available from us upon request. If you need assistance, we will be happy to provide advice and support.

For safe storage we recommend to leave the product in its original packaging, store in a cool, dry place without direct sunlight. The product should be processed within one year from the indicated production date.

All information and recommendations are given by us in good faith on the basis of our practical experience - but without guarantee. We refer to our general terms and conditions of sale and terms of delivery.

For further information, please visit: www.univacco.eu